EDITION: NOVEMBER 2021 B094 | **DECO VARNISH MATT**

REPLACES ALL EARLIER VERSIONS



DECO VARNISH (MATT)

matte water-based varnish for decorative paint work.

- odorless, for indoor and outdoor use
- elastic and resistant
- matte velvet finish

DECO VARNISH (MATT) is a high quality water based varnish. It is odorless, ideal product for indoor and outdoor use. Creates a beautiful matte finish, applied to a number of different surfaces. It is waterproof, has great elasticity and does not peel, swell or break. Protects decorated or sensitive surfaces from frequent use, moisture, abrasions.

COVERAGE
14±2m²/L
FINISH
MATT
THINNING
0-10% WATER
DOVING TIMES
DRYING TIMES
1 hour*
RECOATING TIMES
3-4 hours*
RECOMMENDED NUMBER OF COATS
1-2 coats
TOOLS
roller, brush or airless paint sprayer
,

^{*} Lower temperatures or higher relative humidity will prolong drying and recoating times.



TECHNICAL CHARACTERISTICS

TYPE HYBRID PU SPECIFIC GRAVITY COLORLESS 1.03 ±0,05gr/cm³ SOLIDS w/w (ISO 3251-03) 33±2 % SOLIDS v/v (ISO 3233-98) 31±3 % VISCOSITY (ASTM D 562-05 @ 25°C) KU 100±10 APPLICATION VISCOSITY (ASTM D 562-05 @ 25°C) KU 80±10 pH 8.5±0.5 FLEXIBILITY Mandrel (ISO1519-02) 2mm YELLOWNESS INDEX (ASTM E 313-05) ≤ 0.5 GLOSS (60°) (ISO 2813-99) 4±3 GLOSS (85°) (ISO 2813-99) 20±5 RECOMMENDED DRY FILM THICKNESS 50µm (±5µm) / 2 coats) APPLICATION TEMPERATURE min 5°C-max 30°C	120111110712 01	TARACTERISTICS	<u> </u>
SOLIDS w/w (ISO 3251-03) 33±2 % SOLIDS v/v (ISO 3233-98) 31±3 % VISCOSITY (ASTM D 562-05 @ 25°C) KU 100±10 APPLICATION VISCOSITY (ASTM D 562-05 @ 25°C) KU 80±10 pH 8.5±0.5 FLEXIBILITY Mandrel (ISO1519-02) 2mm YELLOWNESS INDEX (ASTM E 313-05) ≤ 0.5 GLOSS (60°) (ISO 2813-99) 4±3 GLOSS (85°) (ISO 2813-99) 20±5 RECOMMENDED DRY FILM THICKNESS 50µm (±5µm) / 2 coats)	TYPE	HYBRID PU	
SOLIDS v/v (ISO 3233-98) 31±3 % VISCOSITY (ASTM D 562-05 @ 25°C) KU 100±10 APPLICATION VISCOSITY (ASTM D 562-05 @ 25°C) KU 80±10 pH 8.5±0.5 FLEXIBILITY Mandrel (ISO1519-02) 2mm YELLOWNESS INDEX (ASTM E 313-05) ≤ 0.5 GLOSS (60°) (ISO 2813-99) 4±3 GLOSS (85°) (ISO 2813-99) 20±5 RECOMMENDED DRY FILM THICKNESS 50µm (±5µm) / 2 coats)	SPECIFIC GRAVITY	COLORLESS	1.03 ±0,05gr/cm ³
VISCOSITY (ASTM D 562-05 @ 25°C) KU 100±10 APPLICATION VISCOSITY (ASTM D 562-05 @ 25°C) KU 80±10 pH 8.5±0.5 FLEXIBILITY Mandrel (ISO1519-02) 2mm YELLOWNESS INDEX (ASTM E 313-05) ≤ 0.5 GLOSS (60°) (ISO 2813-99) 4±3 GLOSS (85°) (ISO 2813-99) 20±5 RECOMMENDED DRY FILM THICKNESS 50µm (±5µm) / 2 coats)	SOLIDS w/w (ISO 3251-03)		33±2 %
APPLICATION VISCOSITY (ASTM D 562-05 @ KU 80±10 25°C) pH 8.5±0.5 FLEXIBILITY Mandrel (ISO1519-02) 2mm YELLOWNESS INDEX (ASTM E 313-05) ≤ 0.5 GLOSS (60°) (ISO 2813-99) 4±3 GLOSS (85°) (ISO 2813-99) 20±5 RECOMMENDED DRY FILM THICKNESS 50µm (±5µm) / 2 coats)	SOLIDS v/v (ISO 3233-98)		31±3 %
25°C) pH 8.5±0.5 FLEXIBILITY Mandrel (ISO1519-02) YELLOWNESS INDEX (ASTM € 313-05) GLOSS (60°) (ISO 2813-99) GLOSS (85°) (ISO 2813-99) RECOMMENDED DRY FILM THICKNESS EV 80±10 20±5 8.5±0.5 20m 4±3 50pm (±5pm) / 2 coats)	VISCOSITY (ASTM D 562-05 @ 25°C)		KU 100±10
FLEXIBILITY Mandrel (ISO1519-02) 2mm YELLOWNESS INDEX (ASTM E 313-05) ≤ 0.5 GLOSS (60°) (ISO 2813-99) 4±3 GLOSS (85°) (ISO 2813-99) 20±5 RECOMMENDED DRY FILM THICKNESS 50µm (±5µm) / 2 coats)	, ,		KU 80±10
YELLOWNESS INDEX (ASTM E 313-05) ≤ 0.5 GLOSS (60°) (ISO 2813-99) 4±3 GLOSS (85°) (ISO 2813-99) 20±5 RECOMMENDED DRY FILM THICKNESS 50μm (±5μm) / 2 coats)	рН		8.5±0.5
GLOSS (60°) (ISO 2813-99) 4±3 GLOSS (85°) (ISO 2813-99) 20±5 RECOMMENDED DRY FILM THICKNESS 50µm (±5µm) / 2 coats)	FLEXIBILITY Mandrel (ISO1519-02)		2mm
GLOSS (85°) (ISO 2813-99) 20±5 RECOMMENDED DRY FILM THICKNESS 50μm (±5μm) / 2 coats)	YELLOWNESS INDEX (ASTM E 313-05)		≤ 0.5
RECOMMENDED DRY FILM THICKNESS 50µm (±5µm) / 2 coats)	GLOSS (60°) (ISO 2813-99)		4±3
RECOMMENDED DRY FILM I HICKNESS coats)	GLOSS (85°) (ISO 2813-99)		20±5
APPLICATION TEMPERATURE min 5°C-max 30°C	RECOMMENDED DRY FILM THICKNESS		
	APPLICATION TEMPERATURE		min 5°C-max 30°C

DIRECTIVE 2004/42/CE

EU Limit value for this product in a ready-to-use condition (cat A/L: Decorative effect coatings): 200 g/L (2010). This product contains max: 199 g/L VOC.



TECHNICAL DATA SHEET

EDITION: NOVEMBER 2021 B094 | **DECO VARNISH MATT**

REPLACES ALL EARLIER VERSIONS

SURFACE PREPARATION

Carefully prepare surface to obtain good results. Surface must be clean, dry and free from defective or non-cohesive material, dust, oils and salts.

For old and new surfaces:

Apply 1-2 coats of DECO VARNISH in thin coats with a good quality brush. Sand where we deem necessary before application.

INTENDED USE

DECORATION PAINT
FABRIC
WALLPAPERS (NO VINYL)
PLASTER
INTERIOR WOOD
WALL PAINTINGS

APPLICATION

- Stir gently if needed, before and during application.
- The application of DECO VARNISH is done with a brush, roller or airless paint sprayer
- When chalk paint is completely dry, apply the DECO VARNISH.

USEFUL INFORMATION

- ▶ Do not paint when ambient temperature is below 5°C and above 35°C.
- ▶ Ideal product for DECO CHALK finish.
- ▶ Dilute on impregnated surfaces with 10% water for better results

PACKAGING

Containers of 750mL and 375mL.

STORAGE

Two (2) years if unopened and stored under normal storage conditions. Once opened, seal well and store in a closed place at room temperature between 5-30°C. Keep tightly



closed after application for future use. Store in a cool place. Protect against freeze and direct sunlight.

CLEAN-UP / DISPOSAL

Keep your tools wet inside the can when not painting. Rub excess paint off your tools on the side of the can after paint application. Clean tools with hot water and soap immediately after use. Do not empty washing liquids into the water table. Always handle empty containers and product carefully. Do not pour leftover product down the drain. Strictly follow local, regional, national regulations and legislation on the disposal of products and empty containers.

HEALTH & SAFETY

Read carefully the safety instructions on the label. For more information, consult the Safety Data Sheet.





